




RD EUROPE GROUP
ELECTRIC MOTOR COMPONENTS

Specification	R107.5×r75×21.56° × 3.4	Grade	N35SH-1	
Coating	NiCuNi	Quantity		
Inspection Facility	Oven	Samples	3	
Test Standard	Work Time : 2 h Irreversible Loss Rate<3%			
Test Process	NO.	(20±5°C) Magnetic Flux	(120°C) Magnetic Flux	Irreversible Loss Rate
	1	48.0	47.9	0.21%
	2	48.1	47.8	0.62%
	3	48.2	48.0	0.41%
	4			
	5			
	6			
	7			
	8			
	9			
	10			
Max	48.20	48.00	0.41%	
Min	48.00	47.80	0.42%	
Avg	48.10	47.90	0.42%	
Test Result	Test Result: OK			
	Tested:		Verified:  RD EUROPE GROUP ELECTRIC MOTOR COMPONENTS	
Remarks				